

DURAFLEX™ G4 FR SBS

Technical Data Sheet

Product Name: DuraFlex™ G4 FR SBS

Classification: SBS Modified Bitumen Roof Membrane

Product Description: DuraFlex™ G4 FR SBS is a fire-resistant, granule surfaced, premium SBS (Styrene-Butadiene-Styrene) mop or cold applied membrane. Manufactured with a fiberglass mat that is saturated and coated with high quality, asphaltic bitumen and SBS elastomers for a durable, flexible and easily maintainable membrane. It is designed for use as a cap sheet in modified bitumen and hybrid built-up roof systems.

Application Method: DuraFlex™ G4 FR SBS is applied using compatible hot asphalt or SBS cold adhesive.

Approvals: Meets ASTM D 6163 Type I, Grade G. DuraFlex™ G4FR SBS is UL Classified with Underwriter's Laboratories (UL) and is Factory Mutual (FM) Approved. Contact U.S. Ply, Inc. for specific/applicable codes.

Product Data: DuraFlex™ G4 FR SBS (typical)

Thickness: 4.0 mm (157 mils)

Weight: 100 lbs/roll (46 kg/m²)

Roll Dimensions: 39 3/8" x 33' 9" (1m x 10m). Each roll is approximately 1 square applied.

Physical Properties (ASTM D 5147):	Test Results	ASTM D 6163 Minimum
Tensile Strength (lbf/in), 0°F, (MD/XMD)	120/110	70 lbf/in
Tensile Strength (lbf/in), 73°F, (MD/XMD)	105/75	30 lbf/in
Elongation (% @ Max Load), 0°F, (MD/XMD)	4%	1%
Elongation (% @ Max Load), 73°F, (MD/XMD)	3%	2%
Elongation (% @ 5%, Max Load), 73°F, (MD/XMD)	5/7	3%
Tear Strength (lbf), (MD/XMD), 73°F, minimum	105/85	35 lbf
Low Temperature Flexibility, (°F), maximum	0°F (-18°C)	0°F
Dimensional Stability, %, maximum	< 0.2%	1%
High Temperature Stability, (°F)	215°F (101°C)	215°F
Granule Embedment, g/m ² avg. loss	1.3	2g

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative.

U.S. PLY, INC.

A DANNY ADAIR COMPANY

Corporate Headquarters: P.O. Box 11740, Fort Worth, Texas 76110

TOLL-FREE: 866-PUSH-PLY (866) 787-4759 • Local: (817) 413-0103 • Fax: (817) 413-8221

Website: www.usply.com • Email: sales@usply.com

April 2007