

# SAFEWELD™ X4S APP

## Technical Data Sheet

**Product Name:** SAFEWELD™ X4S APP

**Classification:** APP Modified Bitumen Roof Membrane

**Product Description:** SAFEWELD™ X4S APP is a durable smooth surfaced, premium APP (Atactic Polypropylene) cold adhesive applied/hot-air weld membrane. Manufactured with a heavyweight polyester composite and fiberglass mat that is saturated and coated with premium quality, non-blown asphaltic bitumen and APP resins for a durable, heat resistant, flexible and easily maintainable membrane. The top and the bottom surfaces of the sheet are lightly talced to enable the membrane to be applied with SAFEWELD™ APP Modified Adhesive with hot-air heat welded seams. It is designed for use as a base, interply or cap membrane in cold applied APP modified bitumen roof systems.

**Application Method:** SAFEWELD™ X4S APP is applied using SAFEWELD™ APP Modified Adhesive with hot-air heat welded seams.

**Approvals:** Meets ASTM D 6223, Type II Grade S. Contact U.S. Ply, Inc. for specific/applicable codes.

**Product Data:** SAFEWELD™ X4S APP (typical)

Thickness: 4 mm (160 mils)

Weight: 90 lbs/roll (40.8 kg/m<sup>2</sup>)

Roll Dimensions: 39-3/8" x 32' 9" (1m x 10m). Each roll is approximately 108 sq. ft.

### Physical Properties (ASTM D 5147):

Tensile Strength (lbf/in), 0°F, (MD/XMD)

Tensile Strength (lbf/in), 73°F, (MD/XMD)

Elongation (% @ Max Load), 0°F, (MD/XMD)

Elongation (% @ Max Load), 73°F, (MD/XMD)

Tear Strength (lbf), (MD/XMD), 73°F, minimum

Low Temperature Flexibility, (°F), maximum

Dimensional Stability, %, maximum

High Temperature Stability, (°F)

Water Absorption, %, maximum

Moisture Content, %, maximum

### Test Results

202/200

157/150

5/5

4/4

185/180

32°F (0°C)

<0.5%

230°F (110°C)

<0.5%

<0.5%

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative.

***U.S. PLY, INC.***

A DANNY ADAIR COMPANY

Corporate Headquarters: P.O. Box 11740, Fort Worth, Texas 76110

TOLL-FREE: 866-PUSH-PLY (866) 787-4759 • Local: (817) 413-0103 • Fax: (817) 413-8221

Website: [www.usply.com](http://www.usply.com) • Email: [sales@usply.com](mailto:sales@usply.com)

April 2007