

DuraFlex® G4S SBS

PRODUCT DATA SHEET

DuraFlex® G4S SBS is a tough smooth surfaced, premium SBS (Styrene-Butadiene-Styrene) mop or cold applied membrane. Manufactured with a fiberglass mat that is saturated and coated with high quality, asphaltic bitumen and SBS elastomers for a durable, flexible and easily maintainable membrane. It is designed for use as a base sheet or interply sheet in modified bitumen and built-up roof systems.

Physical Properties (ASTM D5147):	Test Results	ASTM D6163 Minimum Standard
Tensile Strength (lbf/in), 0°F (MD/XMD)	120/110 lbf/in	70 lbf/in
Tensile Strength (lbf/in), 73°F (MD/XMD)	105/75 lbf/in	30 lbf/in
Elongation (% @ Max Load), 0°F, (MD/XMD)	4%	1%
Elongation (% @ Max Load), 73°F (MD/XMD)	3%	2%
Elongation (% @ 5% Max Load), 73°F (MD/XMD)	5/7	3%
Tear Strength (lbf), (MD/XMD), 73°F, minimum	105/85 lbf	35 lbf
Low Temperature Flexibility, (°F), maximum	0°F (-18°C)	0°F
Dimensional Stability, %, maximum	<0.2%	1%
High Temperature Stability, (°F)	250°F (121°C)	215°F

Product Data: DuraFlex® G4S SBS (typical)

Thickness: 3.0 mm (120 mils) Weight: 88 lbs/roll (40 kg/m²)

Roll Dimensions: 39 3/8" x 32'9" (1m x 10m)

Each roll is approximately 1 square

Green Standards Information: DuraFlex® G4S SBS contains approximately 16.6% of recycled materials by product weight. Materials are comprised of pre-consumer recycled materials. The pre-consumer recycled materials are derived from reclaimed non-hazardous coal combustion by-product waste which averts disposal of coal by-product waste in landfills or commercial dumps.

Product Name: DuraFlex® G4S SBS

Classification: Meets ASTM D 6163 Type I, Grade S. SBS

Modified Bitumen Base Sheet

Application Method: Applied using compatible hot asphalt

or SBS cold adhesive

Approvals: UL Classified with Underwriter's Laboratories (UL), is Factory Mutual (FM) Approved, and listed with Florida Building Code (FBC) FL-8077, and Texas Department of Insurance (TDI) RC-123. Contact U.S. Ply, Inc. for specific/applicable codes.

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY U.S. PLY, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILI-TY AND FITNESS FOR A PARTICULAR PURPOSE.

