

ALL SEASON® THERMOPLASTIC SEAM SEALER

Description: All Season® Thermoplastic Seam Sealer is a premium synthetic rubber sealant that is “extrudable” for a faster application along seam areas and flashing details. It is strong, very elastic, and adheres to most roofing materials and construction substrates. Available in two grades: Extrudable ‘gun grade’ intended for pump and wand application and a self-leveling grade designed to seal metal roof seams and fasteners without tooling.

Use: Intended for metal roof seams, screw heads, fasteners, vents, and other protrusions and penetrations. Patch and repairing blisters, cracks and seams in existing asphalt, modified bitumen TPO, Hypalon (CSPE), fiberglass, concrete and wood. Ideal for caulking termination bars, flashing & detail flashing.

Product Data:

All Season® Thermoplastic Seam Sealer (typical)

Color: White

% Solids by weight: 56 min.

% Solids by volume: 67 min.

Elongation: 300% min. @ 77°F (25°C)

Weight per gallon: 8.0 lbs.

Flash point (TCC): +100°F (38.7°C)

VOC: < 550 g/L

Container sizes: 5, 55 Gal, 30 oz tube

Surface Preparation: Surfaces to be coated must be clean, paintable and free of foreign materials, oils, grease, mildew and other contaminants that may affect the bonding of the product. It is necessary to wash and prime to enhance adhesion by power washing and broom scrubbing with a diluted solution of USP® PreKote Clean-N-Prime. Rinse clean. Allow a minimum of 30 days weathering of modified bitumen and other asphaltic surfaces to reduce asphalt bleed through. See application specification for more details.

Mixing: Remove lid. **No thinning or reducing is necessary.** Product may separate after shipping and storage, though it may still look mixed. Mechanically mix coating thoroughly and continuously before and during application. For best results, use a 3/4 horsepower or larger electric or air operated mixer with a blade capable of uniformly mixing the entire container. When product is in 5-gallon pails, use a 3” minimum diameter mixing blade. When product is in drums, use a 6” minimum diameter mixing blade.

CORPORATE HEADQUARTERS: P.O. BOX 11740, FORT WORTH, TEXAS 76110

Product Data Sheet



WEATHER PRECAUTIONS:

Temperature:

Air and Surface: 40°F Minimum/120°F Maximum

Material: 50°F Minimum/100°F Maximum

DO NOT APPLY WHEN THE TEMPERATURE CAN FALL TO WITHIN 5°F OF THE DEW POINT WITHIN 6 HOURS.

This product cures by flashing solvents. It is very important that this product is not used when weather conditions are below 40°F or when there is a chance that the temperature could fall below 20°F within a 24 hour period after application. Do not apply this product if rain or dew is likely to occur before drying of product. Late afternoon application is not recommended if high humidity conditions exist, which could cause high moisture concentration of the surface overnight.

Application: Apply to surface at a rate of approximately 1/8” thickness on metal and 1/4” thickness on non-ferrous material. **Extrudable:** Apply to vertical seams at the rate of 40 - 45 lineal feet/gallon approximately 3” wide and 1/8” thick or 30 - 35 lineal feet/gallon approximately 4” wide and 1/8” thick. Apply to horizontal seams at the rate of 20 - 25 lineal feet/gallon approximately 6” wide and 1/8” thick in two coats with USP® PolyForcement embedded between the coating layers. Apply to modified bitumen seams at

TOLL-FREE: 866-PUSH-PLY (866) 787-4759
LOCAL: (817) 413-0103 • FAX: (817) 413-8221
WWW.USPLY.COM

the rate of 15 - 20 lineal feet/gallon approximately 4" wide and 1/4" thick. Tool in place and feather mastic to provide positive slope.

Coverage: Coverage will vary depending on surface and size of area being patched. A thickness of 1/8" is generally sufficient, which represents an application rate of approximately 8 - 10 sq. ft. / gal.

Note: Increased rates of application will prolong the drying time. Do not allow foot traffic until complete dry.

Storage/Handling: Observe normal safeguards for storing and handling of this product prior to and during application. Do not allow coating to freeze. Do not thin with additional solvents. Coating can be applied within an ambient temperature range of 40°F (4.4°C) to 100°F (37.8°C). Store material at 70°F (21.1°C) for at least 24 hours prior to application if the ambient temperature is 50°F (10° C) or below.

Caution: Combustible mixture, keep away from heat, open flame and any source of ignition. Observe normal safeguards for storing and handling of this product prior to and during application. Avoid prolonged contact with skin or flames. If irritation occurs seek medical attention. Cover rooftop air intake vents when applying the primer - to minimize the solvent odor. Use with adequate ventilation and close containers when not in use. If TLV is exceeded, respirators are required (NIOSH/MSHA). Inhalation of high vapor concentration may result in headaches and/or dizziness. Remove individual to fresh air and administer oxygen if breathing is difficult. If breathing has stopped, administer artificial respiration, keep victim warm and order emergency medical attention immediately. If swallowed, do not induce vomiting. Keep out of the reach of children. Read MSDS prior to use.

Clean Up: Keep containers covered when not in use. Clean equipment and spills with mineral spirits or USP® Natural Solvent Cleaner. Clean hands with waterless hand cleaner.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY U.S. PLY, INC. EXPRESSED OR IMPLIED; STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.